

DuPont™ Crastin® SK643FR BK851

THERMOPLASTIC POLYESTER RESIN

Product Information

Crastin® SK643FR BK851 is a 20% Glass Reinforced, Flame Retardant, Polybutylene Terephthalate

General information	Value	Unit	Test Standard
Resin Identification	PBT-GF20FR(17)	-	ISO 1043
Part Marking Code	PBT-GF20FR(17)	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
Molding shrinkage, parallel, annealed	0.6	%	ISO 294-4
Molding shrinkage, normal, annealed	1.45	%	ISO 294-4
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	8300	MPa	ISO 527-1/-2
Stress at break	110	MPa	ISO 527-1/-2
Strain at break	2.8	%	ISO 527-1/-2
Flexural Strength	165	MPa	ISO 178
Charpy impact strength, 73°F	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 73°F	7.6	kJ/m ²	ISO 179/1eA
Thermal properties	Value	Unit	Test Standard
Melting temperature, 18°F/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load, 260 psi	200	°C	ISO 75-1/-2
RTI, electrical			UL 746B
30mil	140	°C	
60mil	140	°C	
120mil	140	°C	
240mil	140	°C	
RTI, impact			UL 746B
30mil	130	°C	
60mil	130	°C	
120mil	130	°C	
240mil	130	°C	
RTI, strength			UL 746B
30mil	140	°C	
60mil	140	°C	
120mil	140	°C	
240mil	140	°C	
Flammability	Value	Unit	Test Standard
Burning Behav. at 60mil nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Oxygen index	32	%	ISO 4589-1/-2
FMVSS Class	DNI	-	ISO 3795 (FMVSS 302)
Electrical properties	Value	Unit	Test Standard
Comparative tracking index	225	-	IEC 60112
Other properties	Value	Unit	Test Standard
Humidity absorption, 80mil	0.13	%	Sim. to ISO 62
Water absorption, 80mil	0.32	%	Sim. to ISO 62
Density	1630	kg/m ³	ISO 1183
Injection	Value	Unit	Test Standard
Drying Recommended	yes	-	-
Drying Temperature	120	°C	-

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Crastin® SK643FR BK851

THERMOPLASTIC POLYESTER RESIN

Drying Time, Dehumidified Dryer	2 - 4 h	-
Processing Moisture Content	≤0.04 %	-
Melt Temperature Optimum	250 °C	-
Min. melt temperature	240 °C	-
Max. melt temperature	260 °C	-
Mold Temperature Optimum	80 °C	-
Min. mold temperature	30 °C	-
Max. mold temperature	130 °C	-
Hold pressure range	≥60 MPa	-
Hold pressure time	3 s/mm	-
Back pressure	As low as possible	-
Ejection temperature	170 °C	-

Characteristics

Regional Availability

- North America
- Europe

- Asia Pacific
- South and Central America

- Near East/Africa
- Global

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11

