

DuPont™ Hytrel® G4078 NC010

THERMOPLASTIC POLYESTER ELASTOMER

Product Information

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow moulding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® G4078 is a low modulus grade with nominal hardness of 40D. It contains non-discoloring stabilizer. It can be processed many conventional thermoplastic processing techniques like injection molding and extrusion.

General information	Value	Unit	Test Standard
Resin Identification	TPC-ET	-	ISO 1043
Part Marking Code	TPC-ET	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Moulding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.1	%	ISO 294-4, 2577
Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile Modulus	55	MPa	ISO 527-1/-2
Stress at 5% strain	2.5	MPa	ISO 527-1/-2
Stress at 10% strain	4.2	MPa	ISO 527-1/-2
Stress at 50% strain	8.5	MPa	ISO 527-1/-2
Stress at break	16	MPa	ISO 527-1/-2
Strain at break	220	%	ISO 527-1/-2
Nominal strain at break	250	%	ISO 527-1/-2
Tear strength, normal	120	kN/m	ISO 34-1
Shore D hardness, 15s	33	-	ISO 7619-1
Mechanical properties	Value	Unit	Test Standard
Charpy notched impact strength, 23 °C	N	kJ/m ²	ISO 179/1eA
Tensile notched impact strength, 23 °C	260	kJ/m ²	ISO 8256/1
Thermal properties	Value	Unit	Test Standard
Melting temperature, 10 °C/min	170	°C	ISO 11357-1/-3
Vicat softening temperature, 50 °C/h, 10N	115	°C	ISO 306
RTI, electrical			UL 746B
0.75mm	50	°C	
1.5mm	50	°C	
3mm	50	°C	
RTI, impact			UL 746B
0.75mm	50	°C	
1.5mm	50	°C	
3mm	50	°C	
RTI, strength			UL 746B
0.75mm	50	°C	
1.5mm	50	°C	
3mm	50	°C	
Flammability	Value	Unit	Test Standard
Burning Behav. at 1.5mm nom. thickn.	HB	class	IEC 60695-11-10

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Hytrel® G4078 NC010

THERMOPLASTIC POLYESTER ELASTOMER

Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Flammability, 3.0mm	HB	-	IEC 60695-11-10
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<100	mm/min	ISO 3795 (FMVSS 302)
Electrical properties	Value	Unit	Test Standard
CTI, 23°C, 3.0mm	600	PLC	UL 746A
Other properties	Value	Unit	Test Standard
Humidity absorption, 2mm	0.7	%	Sim. to ISO 62
Water absorption, 2mm	6.5	%	Sim. to ISO 62
Density	1180	kg/m ³	ISO 1183
Density of melt	1060	kg/m ³	-
Water Absorption, Immersion 24h	3.4	%	Sim. to ISO 62
Film Properties	Value	Unit	Test Standard
WVTR, 23°C/85%r.h.	2000	g/(m ² *d)	DIS 15106-1/-2
Type of extrusion	blown	-	-
Thickness of specimen	0.025	mm	-
Injection	Value	Unit	Test Standard
Drying Recommended	yes	-	-
Drying Temperature	100	°C	-
Drying Time, Dehumidified Dryer	2 - 3	h	-
Processing Moisture Content	≤0.08	%	-
Melt Temperature Optimum	200	°C	-
Min. melt temperature	190	°C	-
Max. melt temperature	220	°C	-
Mold Temperature Optimum	40	°C	-
Min. mould temperature	30	°C	-
Max. mould temperature	40	°C	-
Extrusion	Value	Unit	Test Standard
Drying Temperature	≤80	°C	-
Drying Time, Dehumidified Dryer	2 - 3	h	-
Processing Moisture Content	≤0.06	%	-
Melt Temperature Optimum	195	°C	-
Melt Temperature Range	185 - 200	°C	-

Characteristics

Processing	<ul style="list-style-type: none"> • Injection Moulding • Film Extrusion 	<ul style="list-style-type: none"> • Profile Extrusion • Sheet Extrusion 	<ul style="list-style-type: none"> • Casting • Thermoforming
Delivery form	<ul style="list-style-type: none"> • Pellets 		
Regional Availability	<ul style="list-style-type: none"> • North America • Europe 	<ul style="list-style-type: none"> • Asia Pacific • South and Central America 	<ul style="list-style-type: none"> • Near East/Africa • Global

Revised: 2016-08-17

Page: 2 of 5

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11




Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

DuPont™ Hytel® G4078 NC010


THERMOPLASTIC POLYESTER ELASTOMER

Diagrams

Tensile modulus-temperature



Stress-Strain (TPE)



DuPont™ Hytel® G4078 NC010

THERMOPLASTIC POLYESTER ELASTOMER

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23 °C)
- ✓ Citric Acid solution (10% by mass) (23 °C)
- ✓ Lactic Acid (10% by mass) (23 °C)
- ✗ Hydrochloric Acid (36% by mass) (23 °C)
- ✗ Nitric Acid (40% by mass) (23 °C)
- ✗ Sulfuric Acid (38% by mass) (23 °C)
- ✓ Sulfuric Acid (5% by mass) (23 °C)
- ✗ Chromic Acid solution (40% by mass) (23 °C)

Bases

- ✗ Sodium Hydroxide solution (35% by mass) (23 °C)
- ✓ Sodium Hydroxide solution (1% by mass) (23 °C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23 °C)

Alcohols

- ✓ Isopropyl alcohol (23 °C)
- ✓ Methanol (23 °C)
- ✗ Ethanol (23 °C)

Hydrocarbons

- ✓ n-Hexane (23 °C)
- ✓ Toluene (23 °C)
- ✓ iso-Octane (23 °C)

Ketones

- ✗ Acetone (23 °C)

Ethers

- ✗ Diethyl ether (23 °C)

Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23 °C)
- ✗ SAE 10W40 multigrade motor oil (130 °C)
- ✗ SAE 80/90 hypoid-gear oil (130 °C)
- ✓ Insulating Oil (23 °C)

Standard Fuels

- ✗ ISO 1817 Liquid 1 - E5 (60 °C)
- ✗ ISO 1817 Liquid 2 - M15E4 (60 °C)
- ✗ ISO 1817 Liquid 3 - M3E7 (60 °C)
- ✗ ISO 1817 Liquid 4 - M15 (60 °C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23 °C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23 °C)

Revised: 2016-08-17

Page: 4 of 5

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

DuPont™ Hytrel® G4078 NC010

THERMOPLASTIC POLYESTER ELASTOMER

- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✗ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

Other

- ✓ Ethyl Acetate (23°C)
- ✗ Hydrogen peroxide (23°C)
- ✗ DOT No. 4 Brake fluid (130°C)
- ✗ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ✓ 50% Oleic acid + 50% Olive Oil (23°C)
- ✓ Water (23°C)
- ✗ Water (90°C)
- ✓ Phenol solution (5% by mass) (23°C)

Symbols used:

- ✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

- ✗ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 4mm (Hytrel® measured at 2 mm), IEC Electrical properties measured at 2mm, all ASTM properties measured at 3.2mm, and test temperatures are 23°C unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11

