



Component - Plastics

File Number: E106764

POLYPLASTICS CO LTD

18-1 KONAN 2 CHOME, MINATO TOKYO 1088280 JP



LAPEROS: A410

Liquid Crystal Polymer (LCP), pellets, thermotropic aromatic polyester

| Flammability | Value | Test Method |
|---------------------------------------|-----------------|----------------------|
| Flame Rating | | UL 94 |
| 0.200 mm, NC, BK | V-0 | |
| 0.60 mm, ALL | V-0 | |
| 1.5 mm, ALL | V-0 | |
| 3.0 mm, ALL | V-0 | |
| 6.0 mm, ALL | V-0 | |
| Flammability Classification | | IEC 60695-11-10, -20 |
| 0.200 mm, NC, BK | V-0 | |
| 0.60 mm, ALL | V-0 | |
| 1.5 mm, ALL | V-0 | |
| 3.0 mm, ALL | V-0 | |
| 6.0 mm, ALL | V-0 | |
| Electrical | Value | Test Method |
| Hot-wire Ignition (HWI) | | UL 746 |
| 1.5 mm | PLC 1 | |
| 3.0 mm | PLC 1 | |
| 6.0 mm | PLC 0 | |
| High Amp Arc Ignition (HAI) | | UL 746 |
| 1.5 mm | PLC 4 | |
| 3.0 mm | PLC 4 | |
| 6.0 mm | PLC 4 | |
| Comparative Tracking Index (CTI) | PLC 3 | UL 746 |
| Dielectric Strength | 35 kV/mm | ASTM D149 |
| High Voltage Arc Tracking Rate (HVTR) | PLC 1 | UL 746 |
| Volume Resistivity | 1.0E+15 ohms-cm | ASTM D257 |
| Volume Resistivity | 1.0E+15 ohms-cm | IEC 60093 |
| Arc Resistance | PLC 5 | ASTM D495 |
| Electric Strength | 35 kV/mm | IEC 60243-1 |
| Thermal | Value | Test Method |
| RTI Elec | | UL 746 |
| 0.200 mm | 130 °C | |
| 0.60 mm | 130 °C | |
| 1.5 mm | 130 °C | |
| 3.0 mm | 130 °C | |
| 6.0 mm | 130 °C | |
| RTI Imp | | UL 746 |
| 0.200 mm | 130 °C | |
| 0.60 mm | 130 °C | |
| 1.5 mm | 130 °C | |
| 3.0 mm | 130 °C | |
| 6.0 mm | 130 °C | |

Component - Plastics

File Number: E106764



| Thermal | Value | Test Method |
|-----------------------|--------|-------------|
| RTI Str | | UL 746 |
| 0.200 mm | 130 °C | |
| 0.60 mm | 130 °C | |
| 1.5 mm | 130 °C | |
| 3.0 mm | 130 °C | |
| 6.0 mm | 130 °C | |
| Physical | Value | Test Method |
| Dimensional Stability | 0.0 % | ASTM D1042 |
| Dimensional Stability | 0.0 % | ISO 2796 |

Notice of Disclaimer

By accessing this Yellow Card data information sheet and the database from which this information was generated (the "Yellow Card"), the user acknowledges and accepts the terms and conditions upon which this Yellow Card is made available. This Yellow Card, the database from which it was generated, and all related materials, support, and services, are made available by UL for use only by permission and "as is", without any representation or warranty of any kind, express or implied, including but not limited to any implied warranties of merchantability, fitness for a particular purpose or that the products identified in this Yellow Card will satisfy the user's requirements. UL cannot and does not warrant that the data contained in this Yellow Card is current, accurate, or complete. The user must independently confirm the conformance of any product to the applicable standards or requirements with the manufacturer of that product. Permission to access this Yellow Card may be withdrawn at any time by UL in its sole discretion. The identification of products and companies on this Yellow Card does not in any way imply endorsement of those products or companies by UL. UL does not assume and expressly disclaims, liability to any person for any loss or damage (including lost profits, lost savings, or any indirect, special, incidental, consequential or punitive damages whether or not UL has been advised of the possibility of such damages) arising out of, or in connection with, the use of this Yellow Card regardless of the cause or causes of such loss or damage.